# THIN LZSA GLASS-CERAMIC GLAZE LAYERS FOR DOUBLE FAST FIRING CERAMIC FLOOR TILES

#### <sup>(1)</sup> G. Freitas, <sup>(2)</sup> L. Corradini, <sup>(3)</sup> B.G. Oliveira, <sup>(4)</sup> D. Sighinolfi, <sup>(1)</sup> M. Viana, <sup>(2)</sup> C. Siligardi, <sup>(1)</sup> D. Hotza, <sup>(1)</sup> A.P. Novaes de Oliveira

 <sup>(1)</sup> Universidade Federal de Santa Catarina (UFSC), Florianópolis (SC), Brazil
 <sup>(2)</sup> Università degli Studi di Modena e Reggio Emila (UNIMORE) Modena (MO), Italy
 <sup>(3)</sup> Universidade da Região de Joinville (UNIVILLE), Joinville (SC), Brazil
 <sup>(4)</sup> Expert System Solutions S.r.l. Advanced Laboratory Equipment, Modena (MO), Italy

## **1. INTRODUCTION**

Glass-ceramics are polycrystalline solid materials containing residual glassy phase. [1,2] Such materials show several interesting properties, and have found applications in different areas of society and industry, such as cooktops, cookware and bakeware, protection layers, and sewing-thread supports in the textile industry. [1-3] These materials have also found application in the ceramic tile field. In fact, successful examples of such application are the trademarks "Neoparies" and "Enduro". [1,4] Among glass-ceramic systems of practical interest the LZS (Li<sub>2</sub>O-ZrO<sub>2</sub>-SiO<sub>2</sub>) stands out since the obtained glass and the formed crystalline phases, zircon (ZrSiO<sub>4</sub>) and lithium disilicate (Li<sub>2</sub>Si<sub>2</sub>O<sub>5</sub>), provide glass-ceramic materials with adequate properties for applications such as glazes for ceramic tiles. Previous research works carried out by the authors [5-10] showed that certain compositions of the LZS system exhibit, in particular, high bending strength as well as high abrasion and chemical resistances when compared to traditional materials. Moreover, they are initially white materials, and can be coloured by the introduction of an appropriate inorganic pigment. They are produced at lower temperatures (800-900°C) in short times (35-60 min) using the same conditions and machines of a traditional ceramic factory. However, the utilization of this system is limited by the high coefficient of thermal expansion, CTE (9-11×10<sup>-6</sup> °C<sup>-1</sup>), in comparison to the ceramic bodies  $(5.5-7.0 \times 10^{-6} \text{ °C}^{-1})$ . Therefore, considering that the global CTE of the ceramic system depends on the intrinsic properties of each present crystalline phase, the partial replacement of zirconia with alumina was tested to form the  $\beta$ -spodumeness ( $\beta$ -spodumene solid solution, Li<sub>2</sub>O·Al<sub>2</sub>O<sub>3</sub>·4-10SiO<sub>2</sub>) crystalline phase. [11-13] The  $\beta$ -spodumene (Li<sub>2</sub>O·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub>) crystalline phase shows low CTE ( $0.9 \times 10^{-6} \text{ °C}^{-1}$ ). An appropriate crystallized amount of  $\beta$ -spodumene could compensate the effects caused by other formed crystalline phases, such as zircon (4×10<sup>-6</sup> °C<sup>-1</sup>) and lithium disilicate (11×10<sup>-6</sup> °C<sup>-1</sup>), in particular, decreasing the CTE of the material and originating thus a new glass-ceramic system named LZSA (Li<sub>2</sub>O-ZrO<sub>2</sub>-SiO<sub>2</sub>-Al<sub>2</sub>O<sub>3</sub>) based mainly on  $\beta$ -spodumene and zircon crystalline phases.11-13 In this context and considering the peculiar properties of LZSA glassceramics according to our previous papers, this work shows results regarding thin LZSA glass-ceramic layer glazes obtained by the double fast firing technology. A concentrated suspension containing LZSA parent glass powder and a polymeric liquid base was prepared and applied on fired ceramic bodies by using the screen printing technique. The double firing was conducted in a roller kiln at the 700-1000°C temperature range and firing times between 30 and 120 min. Powder samples were chemically analyzed by X-ray fluorescence (XRF). Sintering behaviour of glass compacts was evaluated by thermal shrinkage measurements in an optical dilatometer (DIL). Crystallization temperature was determined by differential thermal analysis (DTA) and microstructure and glaze layer thickness by scanning electron microscope (SEM). Finally, finished ceramic floor tile samples were evaluated by applying typical ceramic tests. Results indicated that the double fast firing technology, in this case, is an appropriate technical solution for obtaining

sintered thin glass-ceramic glaze layers to produce high performance ceramic floor tiles for a given application.

## 2. EXPERIMENTAL PROCEDURES

A LZSA glass-ceramic frit (19Li<sub>2</sub>O.8ZrO<sub>2</sub>.64SiO<sub>2</sub>.9Al<sub>2</sub>O<sub>3</sub>-molar basis) obtained by melting (1500°C/7h) of industrial raw materials (ZrSiO<sub>4</sub>, Li<sub>2</sub>CO<sub>3</sub>, quartz and natural spodumene) was wet milled in laboratory alumina ball mill (45 h) so that a powder with a average particle size of 10 µm was found by laser scattering analysis (CILAS 1064 L). Chemical composition of the LZSA glass powder was determined by X-ray fluorescence spectroscopy (Philips, PW 2400) and by atomic absorption (UNICAM, Solar 969) for the lithium determination. Thermal linear shrinkage (TLS) of compacted samples was measured by using an optical dilatometer (Expert System Solutions, MISURA ODHT) at 10°C.min<sup>-1</sup> in air. The crystallization temperature of the glass powders were measured using differential thermal analysis, DTA (Netzsch, STA EP 409) in air at a heating rate of 10°C.min<sup>-1</sup> using powdered specimens of about 60 mg in an alumina sample holder with an empty alumina crucible as reference material.

Subsequently, a concentrated suspension containing 56 wt.% LZSA glass powder and 44 wt.% organic media (TF 057/A Manchester) was prepared for screen printing applications on fired industrial ceramic floor tiles. After screen printing applications (110 g/m<sup>2</sup>) ceramic samples were dried at 110°C for 2 h and then they were fired in a roll kiln in the 700-1000°C temperature range for 5 min at the maximum temperature so that the total cycle took from 30 to 120 min, respectively. Selected fired samples were coated with a thin Au film for scanning electron microscopy (SEM) observations (Model Philips XL-30). Additional selected samples were prepared and subjected to typical tests applied to ceramic tiles i.e., chemical resistance, staining resistance, abrasion wear resistance and friction coefficient (Tortus method) according to ISO 10545. The roughness on glazed surfaces before and after abrasion wear was also evaluated.

## 3. RESULTS AND DISCUSSION

Figure 1 shows the linear shrinkage curve of a LZSA glass compact. From figure 1 it can be seen that densification, represented by the liner shrinkage, starts at about 600°C in close agreement to the glass transition temperature (~600°C) determined by DTA, attaining maximum at 850°C when the shrinkage rate tends to zero. This behaviour is related, initially, by the crystallization mainly of zircon, lithium silicates and  $\beta$ -spodumene crystalline phases according to XRD analysis in our previous research works [11-13]. At higher temperatures (>1000°C) crystalline phases are completely melted as shown in figure 1, since shrinkage increases. This behaviour was confirmed also by DTA.



Figure 1. Linear shrinkage of a LZSA glass compact. Heating rate 10 °C.min<sup>-1</sup>.

According to figure 1, DTA and microstructural analysis selected samples were fired at 800°C for 5 min since this was the best condition in terms of porosity and dimensional stability.

In fact, figure 2 shows SEM micrographs related to a sample fired at 800°C for 5 min in which is possible to see a very dense and thin (average thickness of 30  $\mu$ m) LZSA glaze layer respect to the engobe layer and the ceramic body. It is important to point out that the thickness of industrial glazes for ceramic tiles corresponds to about 75-500  $\mu$ m so that 500 to 750 g/m<sup>2</sup> of suspensions are applied.

Preliminary staining tests using chromium and iron oxides on abraded surfaces, after 12,000 revolutions in the abrasion test equipment, show no staining points, indicating that is possible to obtain glazed ceramic floor tiles with optimized porosity for a specific application. Chemical resistance tests show best results (class AA). The measured coefficient of friction was approximately 0.64 in the dry and 0.59 in the wet conditions, respectively.



Figure 2. SEM micrographs of the cross sections of samples fired at 800°C for 5 min at (a) low magnification (ceramic body, engobe-intermediate layer, LZSA glaze-top) and (b) at higher magnification evidencing the LZSA glaze layer on the engobe.

Abrasion wear e chemical resistances results are directly related to the crystalline phases mainly zircon since it has relatively high hardness (7.5 in the Mohs scale) and chemical stability. The high staining resistance, on the other hand, is related to the low porosity observed on the LZSA glazed surfaces and also to the relatively low measured roughness. In fact, surfaces before and after abrasion wear show roughness (Ra) values of 1.44  $\mu$ m and 1.74  $\mu$ m, respectively.

### 4. CONCLUSIONS

LZSA glass-ceramic glazed ceramic floor tiles were obtained by double fast firing at 800°C for 5 min. Relatively thin (30  $\mu$ m) and low porosity glazed layers, applied by the screen printing technique, containing mainly zircon and aluminosilicates crystals were obtained after firing process.

The obtained ceramic floor tiles did not show staining points even after 12,000 revolutions in the abrasion test equipment.

Chemical resistance was class AA, while the coefficient of friction can be appropriate for antislip applications.

On the basis of the preliminary obtained results it is possible to say that the produced ceramic floor tiles are potential candidates in a number of applications but in particular in cases where cleaning is an important requirement.

## ACKNOWLEDGEMENTS

The authors are grateful to Capes and CNPq/Brazil for funding this work.

#### REFERENCES

- [1] Strnad, Z. 'Glass Science and Technology'; 9, 1996, Nueva York, Elsevier.
- [2] Höland, W. and Beall, G. Glass-Ceramic Technology. Publicado por The American Ceramic Society, Westerville, Ohio, 2002.
- [3] Rabinovich, E.M. Review. Preparation of glass by sintering. Journal of Materials Science, 20, 4259-97, 1985.
- Barbieri, L.; Corradi, A.; Leonelli, C.; Manfredini, T. Glass-Ceramics as Tiles Glazes.
  En: Glass-Ceramic Materials, Fundamentals and Applications. Editado por Mucchi, Modena (MO), Italia, 1997.
- [5] Oliveira, A.P.N., Leonelli, C. Properties of glasses belonging to the Li<sub>2</sub>O-ZrO<sub>2</sub>-SiO<sub>2</sub> system. Physics and Chemistry of Glasses, v.39, n.4, p.213-221, 1998.
- [6] Oliveira, A.P.N., Manfredini, T., Pellacani, G.C., Leonelli, C. Sintering and crystallization of a glass powder in the Li<sub>2</sub>O-ZrO<sub>2</sub>-SiO<sub>2</sub> system. Journal of the American Ceramic Society, v.81, n.3, p.777-780, 1998.
- [7] Oliveira, A.P.N., Manfredini, T., Leonelli, C., Pellacani, G.C. Physical properties of quenched glasses in the Li<sub>2</sub>O-ZrO<sub>2</sub>-SiO<sub>2</sub> system. Journal of the American Ceramic Society, v.79, n.4, p.1092-1094, 1996.
- [8] Oliveira, A.P.N., Manfredini, T., Leonelli, C. The effect of the addition of ZrSiO<sub>4</sub> on the crystallization of 30Li<sub>2</sub>O/70SiO<sub>2</sub> powder glass. Thermochimica Acta, v.286, p.375-386, 1996.
- [9] Oliveira, A.P.N., Manfredini, T., Leonelli, C. Sintering, Crystallization and properties of a Li<sub>2</sub>O-ZrO<sub>2</sub>-SiO<sub>2</sub> glass-ceramic for ceramic tile applications. En: V Congreso Mundial de la Calidad del Azulejo y del Pavimento Cerámico - Qualicer 98, Castellón-España, v.2. p.193–204, 1998.
- [10] Oliveira, A.P.N., Manfredini, T., Pellacani, G.C. Vetroceramico preparato mediante sinterizzazione e cristallizzazione di vetro appartenenti al sistema Li<sub>2</sub>O-ZrO<sub>2</sub>-SiO<sub>2</sub> En: IV Congresso Nazionale AIMAT, Cagliari – Italia, 1998.
- [11] Montedo, O.R.K.; Bertan, F.M.; Piccoli, R.; Hotza, D.; Klein, A.N.; Oliveira, A.P.N. Low thermal expansion sintered LZSA glass-ceramics. American Ceramic Society Bulletin, v. 87, N. 7, p. 34-40, 2008.
- [12] Oliveira, A.P.N.; Montedo, O.R.K. Esmaltes Vitrocerâmicos: Características e Soluções Técnicas. Cerâmica Industrial, v. 12, p. 11-14, 2007.
- [13] Montedo, O.R.K.; Oliveira, A.P.N. Relação entre desgaste abrasivo superficial e brilho em porcelanato esmaltado. Cerâmica Industrial, v. 12, p. 14-21, 2007.